Clearcoat WaterbasedClear Sealant



FEATURES

Clearcoat Water Based Clear Sealant & **Graffiti Protection** is based on a premium acrylic emulsion, and is used to provide a durable UV resistant coating for exterior and interior surfaces.

Clearcoat protects a variety of surfaces from graffiti, moisture absorption, dirt retention and household staining.

As **Clearcoat** contains an active biocide, it is resistant to attack by fungi, moss, algae and lichen.

Clearcoat will provide (some) binding properties to friable mineral substrates, and is available in either a Gloss or Matt finish. aloss level achieved will depending on the porosity of the substrate and the film build applied.

RECOMMENDED USES

Clearcoat is suitable for interior and exterior applications, and is particularly useful for the following applications:

Sealing, moisture and stain protection of:

- Masonry
- Fibre Cement sheeting
- Acrylic Painted Surfaces

And as a protective glaze for:

- Terracotta or cement roof tiles
- Terracotta pots
- Exterior stone and masonry
- Hardwood panels
- Roofs painted with acrylic roof coatings such as Cameleon Rooftop
- Pine and cedar panels

SPECIFICATION DATA

Generic Type: Waterborne Acrylic. **Volume Solids:** ~ 22%.

Finish: 40 - 50 μ DFT Matt or Gloss. **Dry Film Thickness:**

Colour: Clear Wet Film Thickness: 180 - 230µ WFT

(1)4 - 12 m² / litre Density: ~1.03 g/cc Coverage:

1 - 2 depending

on substrate.

30 minutes

Dry to Recoat: 2 hours.

Light Foot Traffic: 24 hours.

Full Cure: 7 days.

Packaging: 1,4,10,20,200 litre. Number of coats: Application: Brush, roller or spray. **Touch Dry:** Thinner: Water.

Storage: Store under cool dry conditions.

Water.

Cleanup:

(1)The quantity of Clearcoat required will depend on the absorbency of the substrate. This should be determined onsite by testing a small area of the substrate to be coated.

DIRECTIONS FOR USE

Surfaces should be clean, dry, and free from grease, oil, or other surface contaminants that may hinder the absorbency of **Clearcoat**. Surfaces that are heavily contaminated or contain algal or fungal growth should be thoroughly high pressure water blasted, followed by treatment with Cameleon's **Fungiwash**.

Asbestos surfaces should **NOT** be water blasted, but rather treated directly with Cameleon **Fungiwash** prior to application of the **Clearcoat**.

Normally **Clearcoat** is applied un-thinned, however thinning to a maximum of 10% with water may be required for the first coat on porous surfaces.

The best form of application for large surfaces is flooding by spray to achieve maximum penetration. A minimum of two coats is required to ensure full coverage. Porous surfaces may require further coats for optimum protection. When applying by brush or roller, ensure even coverage is achieved.

Windows and other non-absorbent surfaces should be protected from splashes and over-spray; wash off immediately with water to prevent **Clearcoat** from adhering (as it will be difficult to remove once cured).

*Clearcoat cannot provide total protection against stains and graffiti. Contaminants are easier to remove from surfaces that have been protected by Clearcoat, but ensure that surface contaminants are removed as quickly as possible with a suitable solvent based remover or stripper. The affected area should then be subsequently recoated with Clearcoat to restore to a fully protected surface.

DO NOT apply if temperature is below 10°C, or relative humidity is above 85%.

Typical Specifications

Surface	Preparation		System	Dry Film Build
Concrete and masonry	Thoroughly High Pressure Water Wash.	1.	Clearcoat (thinned 10% with water)	40 - 50µ
		2.	Clearcoat	⁽²⁾ 80 - 100µ
Asbestos Sheeting	DO NOT High Pressure Water Wash.	1. 2.	Fungiwash Clearcoat (thinned 10% with water)	na 40 - 50µ
		3.	Clearcoat	⁽²⁾ 80 - 100µ
Cement and Terracotta Roof	Thoroughly High Pressure Water Wash.	1.	Clearcoat (thinned 10% with water)	40 - 50µ
tiles		2.	Clearcoat	⁽²⁾ 80 - 100µ
Interior Hard Woods	Lightly sand the substrate, especially if it has been previously coated. Ensure surface is clean, dry and dust free.	1.	Clearcoat (thinned 10% with water)	40 - 50µ
		2.	Clearcoat	⁽²⁾ 80 - 100µ

(2)2 coats at 40 - 50 μ DFT per coat recommended.

PRECAUTIONS

See the Safety Data Sheet (SDS) for health and safety information prior to use.

CAMELEON COATINGS

Manufacturers of a complete range of quality paints

A Division of Red Fire Holdings PTY Ltd ABN 65 009 407 381
26 Paramount Drive, Wangara, Western Australia 6065
PO Box 1473, Wangara, Western Australia 6947
Telephone (+61) 8 9302 2577 Fax (+61) 8 9302 2578

email@cameleon.com.au

www.cameleon.com.au

Disclaimer

This is not a specification, and all the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.