TexasModified

AcrylicTextured**Membrane**



FEATURES

Texas Modified is a premium quality acrylic textured coating, modified from standard Texas, for use in special applications.

The main feature of **Texas Modified** is it's ability to bridge fine cracks whilst producing a smooth, fine textured finish which is strong, flexible, durable and washable.

Specifically formulated for interior use where cracks have appeared on plaster walls, **Texas Modified** will dry to a low sheen finish, and is available in a large range of colours.

Texas Modified may also be used for exterior application where a more subtle textured finish is desired than the traditional standard texture coatings.

Water

Water.

Application:

Thinner:

Cleanup:

RECOMMENDED USES

Due to its unique properties, **Texas Modified** is ideal for bridging fine cracks both interior and exterior, and is suitable for application to the following substrates:

- Masonry and cement render
- · Concrete and plaster
- Cement fibre sheeting
- Brick and plaster
- Gyprock
- Brick

SPECIFICATION DATA

Generic Type: Water borne Acrylic. **Volume Solids**: ~41%.

Finish: Low sheen Dry Film Thickness: $*150 - 200 \mu$.

Colour: White and colours **Wet Film Thickness**: *370 - 490 μ.

Density: $1.36 \pm 0.04 \text{ g/cc}$ **Coverage**: *4 - 6 m² / litre

Packaging: 10 litre. Number of coats: 2 coats optimum

Roller and airless **Touch Dry**: 2 - 4 hours

spray **Dry to Recoat**: 12 hours

Hard Dry: 8 - 10 hours.

Storage: Store under cool

dry conditions.

^{*} Note: Due to the texture effect creating a unique "profile", Coverage, WFT and DFT should be taken as a guide only.

DIRECTIONS FOR USE

Ensure all surfaces are clean, dry, and free from oil, grease and dust. The surface should be firm and solid, with loose material removed and large cracks or holes filled. Very smooth or porous surfaces should be primed with Cameleon **Acritec**; or alternatively, apply a prime coat of **Texas Modified** thinned 5 - 10% with water as a seal coat.

Texas Modified is best applied un-thinned, using a medium nap quality roller which will produce uniform thickness and appearance. A fine textured roller can be used to produce a subtle textured effect. When applying by roller, ensure the **Texas Modified** is "laid off" in one direction (downwards) to produce a uniform pattern. Roll closely to the brushed cut-in areas. **Texas Modified** may also be applied by airless spray.

Stir well and ensure colour (if tinted) is as required before use. Provide adequate natural ventilation during use. Wash equipment immediately after use with water.

DO NOT apply if temperature is below 10°C, above 37°C, or relative humidity is above 85%.

Typical Specifications

Surface	Preparation	System	Dry Film Build
Porous and previously painted surfaces	Surfaces should be sanded with all loose flaking paint removed. Ensure that surfaces are clean, dry and dust free.	 Acritec Texas Modified Texas Modified 	50μ 150 - 200μ 150 - 200μ
Masonry, cement render, brick	Ensure that surfaces are clean, dry and dust free.	 Texas Modified Texas Modified 	100 - 150μ 150 - 200μ

PRECAUTIONS

See the Safety Data Sheet (SDS) for health and safety information prior to use.

CAMELEON COATINGS

Manufacturers of a complete range of quality paints

A Division of Red Fire Holdings PTY Ltd ABN 65 009 407 381
26 Paramount Drive, Wangara, Western Australia 6065
PO Box 1473, Wangara, Western Australia 6947
Telephone (+61) 8 9302 2577 Fax (+61) 8 9302 2578

email@cameleon.com.au

www.cameleon.com.au

Disclaimer

This is not a specification, and all the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.