

All Black

General Purpose **Black**



FEATURES

All Black is an economical water based acrylic black coating designed primarily for the coating of steel, but may also be used on a variety of different substrates.

A component of the Cameleon WaterSafe range, **All Black** has been designed as a safer alternative to the traditional economical black shop finishes.

All Black will provide protection against UV, moisture and high humidity for low to medium corrosive atmospheres.

RECOMMENDED USES

The non-flammable, non-toxic nature of **All Black** makes it the ideal coating for use in areas of limited ventilation, or where contamination from solvent based coatings could pose significant problems.

All Black finds uses such as:

- Vehicle chassis
- Implements and machinery
- Tyre black

SPECIFICATION DATA

Colour:	Black	Volume Solids:	~25%
Finish:	Semi-gloss/gloss	Dry Film Thickness:	15 - 30 μ DFT
Density:	~1.04 g/cc	Wet Film Thickness:	60 - 120 μ WFT
Packaging:	20 and 200 litre	Coverage:	2 - 3 m ² / litre @ 30 μ DFT
Application:	Brush, roller or spray	Number of Coats:	1 - 2 coats
Cleanup:	Water	Touch Dry:	30 minutes
Storage:	Store under cool dry conditions.	Dry to Recoat:	4 - 6 hours
		Hard Dry:	4 - 6 hours

PERFORMANCE

Colour Retention:	Excellent
Water Resistance:	Good
Weatherability:	Excellent
Abrasion Resistance:	Good

DIRECTIONS FOR USE

All Black is designed to allow direct to metal application, however, like most acrylic coatings, it may be applied over a previously primed surface as long as they are sound and show good substrate adhesion.

Ensure all surfaces are clean, dry and free from oils, grease or other surface contamination. Un-coated rusty steel should be sandblasted as per recommendations in "Typical Specifications".

All Black may be applied by brush, roller or spray. It is best applied un-thinned, however a maximum of 20% water may be added to aid application.

Stir well before use. Provide adequate natural ventilation during use. Wash equipment immediately after use with Water.

DO NOT apply if temperature is below 10°C, relative humidity is above 85%, or rain is imminent.

PRECAUTIONS

See the Cameleon Coatings General Safety Data Sheet, Product label, and Safety Data Sheet (SDS) for health and safety information prior to use.

CAMELEON COATINGS

Manufacturers of a complete range of quality paints

A Division of Red Fire Holdings PTY Ltd ABN 65 009 407 381
26 Paramount Drive, Wangara, Western Australia 6065
PO Box 1473, Wangara, Western Australia 6947
Telephone (+61) 8 9302 2577 Fax (+61) 8 9302 2578
email@cameleon.com.au
www.cameleon.com.au

Disclaimer

This is not a specification, and all the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.