

Camelastic CSE729

Elastomeric Coating



FEATURES

Camelastic CSE729 is a premium quality, water based elastomeric coating specifically designed for direct to substrate application to a variety of substrates.

Containing a unique extender system in combination with an extremely durable elastomeric polymer system, **Camelastic CSE729** exhibits excellent elongation properties.

Camelastic CSE729 has outstanding adhesion to a wide variety of substrates and the cured film provides excellent strength, durability and flexibility to the coating system. Containing film biocides to eliminate fungal and algal growth, **Camelastic CSE729** will provide long term protection in the harshest of environments.

Camelastic CSE729 has been tested and passes all CBH Testing Protocols.

RECOMMENDED USES

Camelastic CSE729 is suitable for interior or exterior applications. It can be applied to exterior surfaces to provide a protective film that can cope with the expansion and contraction that may be experienced on large roof surfaces. It can be applied directly to the following surfaces:

- Galvanised Iron
- Aluminium
- Concrete and cement render
- Colourbond
- Timber
- Fibre cement sheets

Camelastic CSE729 may be applied at very high dry film build, in some circumstances up to 5000 microns. **Camelastic CSE729** has been designed for wet on wet applied to WFT above 8000 microns with excellent hold up and minimal slumping. This feature allows **Camelastic CSE729** to be applied to roof sheeting and structure on the internal, underside of structures, in particular grain storages.

SPECIFICATION DATA

Colour:	White & Grey	WFT:	~1800µ WFT for 1000µ DFT
Density:	~ 1.26g/cc		~9000µ WFT for 5000µ DFT
Volume Solids:	~56%	Coverage:	1 m ² / litre @ 500µ DFT
Weight Solids (NVM):	~66%	Number of Coats:	1 - 3 coats
Packaging:	20,200, 1000 litre	Touch Dry:	1 hour @ 500µ DFT at 25°C
Application:	Airless spray, brush or roller	Dry to Recoat:	24 hours (if required)
Cleanup:	Water	Hard Dry:	8 hours @ 500µ DFT at 25°C
Storage:	Store under cool dry conditions.		

PERFORMANCE

Temperature Resistance:	Excellent
Abrasion Resistance:	Good
Weatherability:	Excellent
Colour Retention:	Excellent
Water Resistance:	Excellent
Heat Resistance:	Laboratory tested to withstand dry heat up to 90°C

DIRECTIONS FOR USE

Ensure all surfaces are clean, dry, and free from contamination, including fungal or algal growth.

Camelastic CSE729 is best applied by airless spray using a minimum pump ratio of 30:1. Spray sufficient coats wet on wet to achieve the required film build. The product will easily build to 3200µ High Volume Low Pressure (HVLP) spray system can be used for internal application at very high wet film builds.

Stir thoroughly before use - apply un-thinned, however **Camelastic CSE729** may be thinned 5 - 10% with water to aid application, if required for specific situations.

Application by roller should be with a textured sleeve.

Large external areas such as roofs should be high pressure water blasted to remove any residual dirt, fungal or algal growth.

Provide adequate natural ventilation during use. Wash equipment immediately after use with water.

DO NOT apply if temperature is below 10°C or if relative humidity is >85% or rain is imminent.

Typical Specifications

Surface	*Preparation	System	Dry Film Build
Plaster, masonry, brick, cement, cement render, fibre sheeting, and wood or galvanised metal.	Thoroughly clean the surface ensuring all traces of loose material and surface contamination (oil, grease etc) are removed.	1. Camelastic CSE729	2500 µ
	Remove any flaking or peeling paint, fill and sand surface (if required). <i>Prepare galvanised or steel surfaces to SSPC-SP-1</i>	2. Camelastic CSE729 Wet on Wet application is possible internally.	2500µ

PRECAUTIONS

See the Safety Data Sheet (SDS) for health and safety information prior to use.

CAMELEON COATINGS

Manufacturers of a complete range of quality paints

A Division of Red Fire Holdings PTY Ltd ABN 65 009 407 381
26 Paramount Drive, Wangara, Western Australia 6065
PO Box 1473, Wangara, Western Australia 6947
Telephone (+61) 8 9302 2577 Fax (+61) 8 9302 2578
email@cameleon.com.au
www.cameleon.com.au

Disclaimer

This is not a specification, and all the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.