

# Texas

## Acrylic Textured Membrane



### FEATURES

**Texas** is a premium quality acrylic textured membrane coating exhibiting excellent moisture and UV resistance.

**Texas** has been specifically formulated for both interior and exterior application, and will provide a tough, flexible, abrasion resistant coating with excellent durability.

Due to its unique consistency and low sheen, **Texas** allows a uniform textured finish that will bridge hairline cracks, and allow imperfect and uneven surfaces to be hidden.

### RECOMMENDED USES

Due to its unique properties, **Texas** is ideal for application to uneven, imperfect substrates both interior and exterior, and is suitable for application to the following substrates:

- Masonry and cement render
- Concrete and plaster
- Cement fibre sheeting
- Brick and plaster
- Galvanised iron
- Gyprock

### SPECIFICATION DATA

<b>Generic Type:</b>	Water borne Acrylic.	<b>Volume Solids:</b>	41%.
<b>Finish:</b>	Low sheen	<b>Dry Film Thickness:</b>	*225 – 250 $\mu$ .
<b>Colour:</b>	White.	<b>Wet Film Thickness:</b>	*550 - 610 $\mu$ .
<b>Density:</b>	1.36 $\pm$ 0.04 g/cc	<b>Coverage:</b>	*1 - 3 m <sup>2</sup> / litre per coat
<b>Packaging:</b>	4,10 and 20 litre.	<b>Number of coats:</b>	2 coats optimum
<b>Application:</b>	Roller and airless spray	<b>Touch Dry:</b>	2 - 4 hours
<b>Thinner:</b>	Water	<b>Dry to Recoat:</b>	24 hours
<b>Cleanup:</b>	Water.	<b>Hard Dry:</b>	8 - 10 hours.
		<b>Storage:</b>	Store under cool dry conditions.

*\* Note: Due to the texture effect creating a unique "profile", Coverage, WFT and DFT should be taken as a guide only.*

## DIRECTIONS FOR USE

Ensure all surfaces are clean, dry, and free from oil, grease and dust. The surface should be firm and solid, with loose material removed and large cracks or holes filled. Very smooth or porous surfaces should be primed with Cameleon **Acritec**; or alternatively, apply a prime coat of **Texas** thinned 10 - 15% with water as a seal coat.

**Texas** is best applied un-diluted, using a foam textured roller which will produce uniform thickness and appearance. When applying by roller, ensure the **Texas** is "laid off" in one direction (downwards) to produce a uniform pattern. **Texas** may also be applied by airless spray.

Stir well and ensure colour (if tinted) is as required before use. Provide adequate natural ventilation during use. Wash equipment immediately after use with water.

**DO NOT apply if temperature is below 10°C, or relative humidity is above 85%.**

### Typical Specifications

Surface	Preparation	System	Dry Film Build
Porous and previously painted surfaces	Surfaces should be sanded with all loose flaking paint removed. Ensure that surfaces are clean, dry and dust free.	1. Acritec 2. Texas 3. Texas	50µ 225 - 250µ 225 - 250µ
Masonry, cement render, brick	Ensure that surfaces are clean, dry and dust free.	1. Texas 2. Texas	225 - 250µ 225 - 250µ
Steel or galvanised surfaces	Thoroughly scrub the surface to remove any white corrosion products and surface contamination (oil, grease etc). Prepare substrate to SSPC-SP-1.	1. Galvaprim WB137 2. Texas 3. Texas	25 - 30µ 225 - 250µ 225 - 250µ

## PRECAUTIONS

See the Safety Data Sheet (SDS) for health and safety information prior to use.

## CAMELEON COATINGS

### Manufacturers of a complete range of quality paints

A Division of Red Fire Holdings PTY Ltd ABN 65 009 407 381  
26 Paramount Drive, Wangara, Western Australia 6065  
PO Box 1473, Wangara, Western Australia 6947  
Telephone (+61) 8 9302 2577 Fax (+61) 8 9302 2578  
[email@cameleon.com.au](mailto:email@cameleon.com.au)  
[www.cameleon.com.au](http://www.cameleon.com.au)

#### Disclaimer

This is not a specification, and all the information is given in good faith. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated, the manner of use and whether there is any infringement of patents is the sole responsibility of the user. The manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. For application in special conditions, consult the manufacturer for detailed recommendations.